



## TECHNICAL DATA SHEET

rev. 00 06/07/2007

## STUCCO ISOLANTE (bonding agent)

code FO3410

### TECHNICAL DATA *(based on room temperature of +23° C and 65% of relative air humidity)*

Appearance	trasparent liquid
Viscosity	18" F4 ± 2" F4
Specific weight	0.93 ± 0.01
Superficial drying ♦	15 - 30 min.
Dry for abrading after ♦	1 - 2 hrs
Complete drying	2 hrs
Recommended coverage (per coat) ♦	8 - 12 m <sup>2</sup> /lt
Thinning	DILUENTE V3a
Tools cleaning	DILUENTE LAVAGGIO
VOC content %	89 %

♦ depending on the wood species, on how abrading is effected and on the quantity of absorbed product

### DESCRIPTION

Single-component, nitrosynthetic, bonding agent in acetate solvents to prepare a fast sanded filler for smoothing parquet.

Ready-to-use product.

**Standard packaging:** 10-lt can.

### DIRECTIONS

Sand the floor with coarse- and medium grained abrasive. Mix STUCCO ISOLANTE with the necessary quantity of sawdust from the sanding to form an homogeneous paste. Spread it quickly using a stainless, wide spatula (American spatula), pushing as much filler as possible into the cracks. After drying, which normally requires 1 hour, sand with fine abrasive, then vacuum and tack thoroughly. Apply one of our solvent-based finishing cycles.

### NOTICE

- Before application, allow the wood and the product to reach a temperature between +15°C and +35°C.
- The support to be treated should have a moisture content inferior to 12%.
- The product is highly flammable. Ventilate the rooms before sanding.
- STUCCO ISOLANTE can not be used with waterborne finishes.

**Dispose of excess product and empty containers properly!**

If the original unopened container is stored in a cool and dry place, the product will keep for at least 12 months.

*The information contained in this technical data sheet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.*