

CARVER S.r.l.
Via Giovanni XXIII, 36
20090 Rodano (MI) ITALY
Tel. (02) 95.00171 (r.a.)
Fax (02) 95.320.921
internet: www.carver.it



AZIENDA CON SISTEMA DI
GESTIONE PER LA QUALITÀ
CERTIFICATO DA DNV
= UNI EN ISO 9001:2000 =

AZIENDA CON SISTEMA DI GESTIONE
AMBIENTALE CERTIFICATO DA DNV
= UNI EN ISO 14001:2004 =

TECHNICAL DATA SHEET

rev. 00 of 17/03/2009

COMPLET (fungicide and anti-woodworm)

code MO4000

TECHNICAL DATA (based on room temperature of +23° C and 65% of relative air humidity)

Viscosity	10" F4 ± 2" F4
Specific weight	0.8 ± 0.1
Recoating after / within (brush or spray gun)	12 / 72 hr
Recoating after / within (immersion)	24 / 72 hr
Coverage (per coat) ♦	5 - 10 m ² /litre
Thinning and tools cleaning	DILUENTE LINOLUX
Max. allowed thinning rate	100 %
VOC %	99.0% ± 0.5%

♦ depending on the wood species, on how abrading is effected and on the absorbed product amount.

DESCRIPTION

Worm-fighting fungicide to disinfect the wood from xylophage insects (woodworm, capricorn, lynktus, wood-ant, termite, etc.) in curative as well as in preventive form. This product meets the requirements of the Italian Ministry of Health (authorisation No. 18563).

COMPLET can be over-coated with all Carver interior/exterior products on water and on solvent base

Standard packaging: 5-litre plastic can.

APPLICATION

Sand the surface with #100÷120-grit abrasives, removing all wax, oil or existing finish. Vacuum and tack thoroughly, then apply 1 or 2 abundant coats of COMPLET by brush or spray, or else by immersion.

Without abrading, apply 1 coat of the sealer or finish you have chosen, adhering to the prescribed recoating schedule. Abrade now, then apply the following finishing coats.

NOTICE

- The wood to be treated should have a moisture content inferior to 20%.

Dispose of excess product and empty containers properly!

If the original unopened container is stored in a cool and dry place, the product will keep for at least 12 months.

N.B. The information contained in this technical leaflet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.