

CARVER S.r.l.
Via Giovanni XXIII, 36
20090 Rodano (MI) ITALY
Tel. (02) 95.00171 (r.a.)
Fax (02) 95.320.921
internet: www.carver.it



AZIENDA CON SISTEMA DI GESTIONE
AMBIENTALE CERTIFICATO DA DNV
= UNI EN ISO 14001:2004 =

AZIENDA CON SISTEMA DI GESTIONE
PER LA QUALITÀ CERTIFICATO DA DNV
= UNI EN ISO 9001:2008 =

TECHNICAL DATASHEET

rev. 01 2010/04/06

OILPAST (concentrated paste)

code SO8400 BI/BL/GI/NE/RO

TECHNICAL DATA

(based on room temperature of +23°C and 65% of relative air humidity)

Appearance	thixotropic coloured paste
Highest addition percentage	20 %
Cleaning of tools	DILUENTE LINOLUX
Solids content	74 ± 6 %
VOC	26 ± 6 %

DESCRIPTION

Concentrated coloured pastes in 5 colours (white, blue, yellow, black and red) for colouring or modifying the colour of PRIMOL, GREENOL, BIOREXOL, EXTEROL, CARVEX, POLICARVER and of oil systems in general. All pastes can be mixed for custom colours.

DIRECTIONS

Add the paste to the product to be coloured and mix thoroughly until you obtain a homogeneous, settlingfree solution. Apply the solution by pad or cloth then complete the application cycle with the respective transparent finishes (GREENOL, POLICARVER, BIOWAX, EXTEROL). Should a **white** colouring be required, it is **necessary** to add the OILPAST BIANCO white paste not only for the priming coat but also for the finish coat. Application should always be made in thin coat.

NOTICE

- **If used alone, the pastes cannot dry. They should be employed only in addition to siccative products.**
- It is **essential** to use the product at temperatures not below +15°C. Let product reach at least this temperature before use.
- Pastes' colors are indicative. The achieved wood colouring depends on the wood species and structure and may vary in time due to external factors.
- **Soak used rags and cloths in water immediately after use to prevent spontaneous combustion.**

Dispose of excess product and empty containers properly.

If the original unopened container is stored in a cool dry place, the product will keep for at least 12 months.

The information contained in this technical leaflet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.