





### Recommended cycles:

- **To preserve the natural colour of the wood:** apply META with Carver FONDO 300 waterborne sealer (see the technical data sheet of this product).
- **To get a wood toning similar to a solvent-based finish cycle:** apply META with one of Carver waterborne sealers GIOTTO or RAFFAELLO (see the technical data sheets of these products).
- **To obtain a wood toning typical for a solvent-based finish cycle:** apply 1 coat of Carver FONDO K2 two-component, solvent-based, polyurethane sealer (see the technical data sheet of this product). After 3 and before 24 hours abrade with #150÷180-grit abrasive, **taking care not to “break through”**, then apply 1 final coat of META.
- **To achieve a high-performance water-based cycle:** apply 2-3 coats of META, abrading between coats and adhering to the prescribed schedule.
- **To achieve a rapid water-based cycle:** apply META with Carver FAST 2004 waterborne sealer (see the technical data sheet of this product).
- **In case of exotic or little absorbing woods**, such as wengé, ipé lapacho, olive etc., we recommend to give a priming coat with FONDO 300 sealer to improve adhesion and to avoid any unwanted wood colour change.

**Any different cycle or applying method should be previously verified.**

#150÷180-grit abrasives are recommended for a single-plate machine (buffer); when employing a Trio sander, use #80÷100-grit abrasives.

### **NOTICE**

- Apply at a room temperature between +15°C and +35°C with a relative humidity rate between 35% and 80%. Allow finish to reach room temperature before application.
- **Before application make sure the hardener is completely dissolved in the finish** (there is always a little increase of the mixture viscosity).
- **Adhere to the recommended coverage rates.**
- Always adhere to the prescribed recoating and abrading schedule. When recoating without abrading do not exceed 7 hrs interval from the previous coat. When abrading and recoating do not exceed 48 hrs interval. **After abrading, always vacuum and tack thoroughly.**
- To improve the flow and to extend the open time, particularly during warmer weather, add to the catalyzed finish 2% of Carver DILUENTE A60 additive or (max.) 5% of Carver ACQUA BLU thinner.
- Clean tools with Carver IDROCLEANER or, for want of this, with water, better if lukewarm.
- **The finished surface can be cautiously walked on after 24 hours. It achieves the optimal physical resistance after 8 - 10 days.**

### **Protect from freezing!**

Dispose of excess product and empty containers properly.

If the original unopened containers are stored in a cool and dry place, the product will keep for 8 months.

*The information contained in this technical data sheet is to the best of our knowledge and experience. Since the conditions of use are beyond our control, no warranty is given or implied.*